

Alekh

PLASTICS TESTING SERVICES

F-95, Rudraksha-II, Phase-3, GIDC, Vatva, Ahmedabad: 382445

Tel: 79-25830445, e-Mail: alekh_plastics@yahoo.com

TEST REPORT

No: TR/24-25/0582ARev.

Date: 22/08/2024

Issued to: M/s. Reco Solutions

Date of receipt: 25/07/2024

GIDC Estate,

Date of completion: 05/08/2024

Gandhinagar

Sampling by: Customer

Sample details: Recycled Black sheet (as stated by the party)

Sample Packing: Loose

Mode of delivery: By hand

Your reference: Personal visit on 25/07/24

Test result

Sample	Test Property	Unit	Test method	Test value
Sample as above	Tensile breaking load	kg/cm ²	IS:13360-5-1	57
	Elongation at break	%	---do---	17
	Flexural strength	kg/cm ²	IS:13360-5-7	193
	Compressive strength	kg/cm ²	IS:13360-5-8	165
	Flammability			
	-Burning rate	mm/sec	IS:13360-6-4	<5 (0.6)
	Screw holding strength	N	Across face	1142
	Thermal resistance	---	At 85°C/30min	No effect



Authorised Signatory

B. R. Phadnis

Chief Executive

N.B.: No liabilities are accepted, whatsoever, for this test report. Valid only for the sample tested. Not for publication/legal purpose.

~~~~~ END OF REPORT ~~~~~

.....making testing simple!